

Amendments to the Specification:

Please insert the following paragraph beginning on page 6, line 1:
 wherein x is an integer from about 1 to about 100, y is an integer from about 1 to about 100, and z is an integer from about 1 to about 100.

Please replace Table 9 on page 24 with the following amended Table 9:

TABLE 9

Examples	<u>2325</u>	<u>2426</u>	<u>2527</u>	<u>2628</u>
Tensile Strength PSI ASTM D-638	2541	2430	2720	3610
% Elongation ASTM D-638	235	265	420	350
Tear Strength P.L.I. ASTM D-624	357	340	510	550
Shore Hardness D ASTM D2240-81	47/40	47/40	47/40	47/40
Abrasion HS-18 Wheel 1000gm – 1000 cycle ASTM D-4060	0.6mg loss	0.6mg loss	0.4mg loss	0.4mg loss
Elcometer PSI	-	-	-	-
Concrete	450	375	750	900
Steel ASTM 4551	>1000	>1000	>1300	>1500
Moisture Vapor Transmission (Perms) ASTM E96-80	<0.1	<0.1	<0.1	<0.1
Water Absorption WT Gain ASTM D570-95	1.90%	2.20%	1.25%	0.85%

Serial No. 10/648,934
 Amendment and Remarks Responsive To
 Office Action Mailed 05/13/05
 Page 2 of 17